

# ROYAL ER 317L (ER 317L)

AWS –SFA A 5.9 ER 317L EN ISO 14343 A G/W 19 12 3 L

## Applications

It is used for welding of AISI 317 , ASME 317L type of plate sheet, pipes tubes used in fabricating equipments for chemical, pharmaceutical, Dairy & fertilizer, Industries, Oil Refineries, Specially used for root run .

## Characteristics on Usage

This wire rods with low carbon content confirms to AWS – SFA 5.9 ER 317L class. The weld metal is very good resistant to inter granular corrosion without the use of stabilizer such as Niobium or titanium; free from porosity & molten pool. The weld metal is of controlled ferrite & with stand working temp up to 300 C Scale resistant up to 800 C..

## Packing

Each Packets content 5 kg of Wire Rods having length 500 mm.,1000mm.

MIG TIG WIRES

## Chemical Composition Of Weld Metal

C%	Mn%	Si%	S%	P%	Cr %	Ni %	Mo %
0.030 Max	1.0 - 2.50	0.30 - 0.65	0.030 Max	0.030 Max	18.5 - 20.5	13.0 - 15.0	3.0 - 4.0

## Mechanical Properties Of Weld Metal

U.T.S. (N/mm <sup>2</sup> )	ELONGATION ( L = 4d ) %
520 Min	30 % Min