

ROYAL ER NiCrMo3 (ER NiCrMo3)

AWS –SFA A 5.14 ER NiCrMo3 EN ISO 18274 A S Ni 6625

Applications

It is used for welding of Nickel, chromium & molybdenum alloy ASTM B443, B444 & B446 steel with other Nickel base alloys for cladding steel with Ni-Cr-Mo weld metal This filler metal is recommended for application where the operating temp. ranges from cryogenic to 1000 F (540 °C)

Characteristics on Usage

Royal ER NiCrMo3 – Nickel alloys solid filler Wire Rods deposit 61% Ni, 22% Cr, 9% Mo, 3.5 % Nb+ Ta This type of filler wire rod is used for welding of Nickel Chromium & Molybdenum alloys steel for surfacing steel with nickel chromium molybdenum weld metal.

Packing

Each packet contents 5 kg. of wire Rods. Special packing will be supply on request.

Approvals

B.V.

MIG TIG WIRES

Chemical Composition Of Weld Metal

C%	Mn%	Si%	S%	P%	Cr %	Ni %	Mo %
0.10 Max	0.50 Max	0.50 Max	0.015 Max	0.020 Max	20.0 – 23.0	58 Min	8.0 - 10.0

Mechanical Properties Of Weld Metal

U.T.S. (N/mm ²)	ELONGATION (L = 4d) %
760 Min.	30 Min,