

# ROYAL C - V


## Applications

Concrete mixer blades. Excavator teeth plough shares. Bucket lips, scraper blades. Cement die, rings.

## Characteristics on Usage

This is a medium coated Rutile type hard facing electrode depositing on air hardening, weld metal is of approximately 600 BHN hardness. The weld metal resistant to severe abrasion and moderate impact, suitable for hardfacing applications like Dredger bucket lips, plough shares, excavator, conveyor buckets etc.,

## Welding Positions



## Notes On Usage

- ⌚ Dry the electrodes at 70-100o C for 60 minute before use.
- ⌚ Preheat at 150o C or more than that in general.

## Chemical Composition Of Weld Metal

C%	Mn%	Si%	S%	P%	Cr %
2.20 -2.80	0.80 - 1.25	2.50- 3.50	0.030 Max	0.030 Max	3.0- 4.0

## Packing and Welding Current

SIZE ( mm )	KG PER PACKET	KG PER CARTON	LBS PER PACKET	LBS PER CARTON	In Amps	Current (Amps)
2.50 x 350	5	20	11	44	70 - 90	AC / DC (+)
3.20 x 450	5	20	11	44	100 - 140	
4.00 x 450	5	20	11	44	140 - 180	
5.00 x 450	5	20	11	44	180 -- 210	

TYPICAL WELD METAL HARDNESS IS 575 - 600 BHN.